

Características Técnicas

TO :

ATT. : Controle de Qualidade

DATE : 29/10/2021

Papel Alcalino

		Mínimo	Meta	Máximo		
Alvura Feltro (S/F)	ISO	96,0	98,0		ISO-2470	N
Aspereza (MP4) - F	ml/min		175,0	325,0	ISO-8791	N
Aspereza (MP4) - T	ml/min		175,0	325,0	ISO-8791	N
Aspereza Bendtsen F	mL/min		175,0	325,0	ISO-8791	N
Aspereza Bendtsen T	mL/min		175,0	325,0	ISO-8791	N
Brancura Feltro	D65 10°	156,0	158,0	161,1	ISO-11475	N
Cobb (60 seg)	g/m ²		30,0	41,0	ISO-535	N
Espessura	mm	0,061	0,065	0,069	ISO-534	N
Gramatura	g/m ²	48,0	50,0	52,0	ISO-536	N
Opacidade (ISO)	%	76,0	78,0		ISO-2471	N
Porosidade Gurley	s/100cc	7,0	12,0	18,0	TAPPI-460	N
Umidade	%	4,9	6,0	7,1	ISO-287	N

Atenciosamente

JOYCE F ALVES FRANCATO

Controle de Qualidade

PAPEL - PAPEL CHAMBRIL 50.0

Tonalidade

Condições de Testes

Standard IPB

ISO 187/00

BIL050 - Rev. 115 - STD