

Características Técnicas

TO :

ATT. : Controle de Qualidade

DATE : 29/10/2021

Papel Alcalino

		Mínimo	Meta	Máximo		
Alvura Feltro (S/F)	ISO	96,0	98,0		ISO-2470	N
Aspereza (MP4) - F	ml/min		175,0	325,0	ISO-8791	N
Aspereza (MP4) - T	ml/min		175,0	325,0	ISO-8791	N
Aspereza Bendtsen F	mL/min		175,0	325,0	ISO-8791	N
Aspereza Bendtsen T	mL/min		175,0	325,0	ISO-8791	N
Brancura Feltro	D65 10°	158,0	161,0	164,0	ISO-11475	N
Cobb (60 seg)	g/m ²		30,0	40,0	ISO-535	N
Espessura	mm	0,068	0,073	0,078	ISO-534	N
Gramatura	g/m ²	53,8	56,0	58,2	ISO-536	N
Opacidade (ISO)	%	79,0	81,0		ISO-2471	N
Porosidade Gurley	s/100cc	7,0	12,0	18,0	TAPPI-460	N
Umidade	%	5,0	6,0	7,0	ISO-287	N

Atenciosamente

JOYCE F ALVES FRANCATO

Controle de Qualidade

PAPEL - PAPEL CHAMBRIL 56.0

Tonalidade

Condições de Testes

Standard IPB

ISO 187/00

BIL056 - Rev. 98 - STD