

BACKLIT		
CHARACTERISTICS	DATA	TEST METHOD
Weight	510 g/m ²	ISO 3801:1977
Polyester Fabric	300×500 denier 18×12 fd per inch	DIN60001: 2001-05 /DIN EN ISO2060: 1994
Type of Coating	PVC	N/A
Tensile Strength	650 N/5cm (L)	ISO527/3:2018
	440 N/5cm (W)	
Tear Strength	50 N/5cm (L)	ISO4674/1:2016
	25 N/5cm (W)	
Adhesion Strength	N/A	DIN53357:1982
Low Temperature	N/A	DIN EN 1876-1:1998
RF Weldable (Heat Sealable)	YES	DIN53354:1981

APPLICATIONS:	Building Wraps, Fence Graphics, Stadium Graphics, Barricade Graphics, Street Graphics, Indoor Graphics, Outdoor Graphics
INK COMPATIBILITY:	Solvent, Eco-Solvent