

Technical Characteristics

TO : KLEIBER
 ATT. : Controle de Qualidade
 DATE : 31/07/2020

Alkaline Paper

		Minimum	Target	Maximum		
Blancura (CIE)	D65 10°	158,0	161,0	164,0	ISO-11475	N
Blancura (S/F)	ISO	96,0	98,0		ISO-2470	N
Cobb F (120 Seg)	g/m ²		30,0	41,0	ISO-535	N
Cobb T (120 Seg)	g/m ²		30,0	41,0	ISO-535	N
Espesor	mm	0,143	0,150	0,156	ISO-534	N
Gramage	g/m ²	115,2	120,0	124,8	ISO-536	N
Humedad	%	4,9	6,0	7,0	ISO-287	N
Opacidad	%	95,0	97,0		ISO-2471	N
Porosidad Gurley	s/100cc	15,0	24,0	33,0	TAPPI-460	N
Rugosidad F	mL/min		175,0	325,0	ISO-8791	N
Rugosidad T	mL/min		175,0	325,0	ISO-8791	N

Sincerely

EDER JUNIOR BARROSO

Quality Control

PAPER - PAPEL CHAMBRIL 120.0

Shade

Conditioning of samples

Standard IPB
 ISO 187/00
 BAL120 - Rev. 1 - STD