

## Technical Characteristics

TO : KLEIBER  
 ATT. : Controle de Qualidade  
 DATE : 31/07/2020

### Alkaline Paper

		Minimum	Target	Maximum		
Blancura (CIE)	D65 10°	158,0	161,0	164,0	ISO-11475	N
Blancura (S/F)	ISO	96,0	98,0		ISO-2470	N
Cobb (120 Seg)	g/m <sup>2</sup>		30,0	41,0	ISO-535	N
Cobb (120 Seg)	g/m <sup>2</sup>		30,0	41,0	ISO-535	N
Espesor	mm	0,278	0,293	0,309	ISO-534	N
Gramage	g/m <sup>2</sup>	230,4	240,0	249,6	ISO-536	N
Humedad	%	4,9	6,0	7,0	ISO-287	N
Opacidad	%	97,0	99,0		ISO-2471	N
Porosidad Gurley	s/100cc	17,0	27,0	37,0	TAPPI-460	N
Rugosidad F	mL/min		250,0	400,0	ISO-8791	N
Rugosidad T	mL/min		250,0	400,0	ISO-8791	N

Sincerely

EDER JUNIOR BARROSO

Quality Control

**PAPER - PAPEL CHAMBRIL 240.0**

Shade

Conditioning of samples

Standard IPB

ISO 187/00

BAL240 - Rev. 1 - STD