

Para : International Paper
Att : José Ricci
Fecha : 17 de junio de 2020
Papel : **Chambril 50.0**

		Mínimo	Meta	Máximo	
Gramage	g/m ²	47.8	50.0	52.0	ISO-536
Espesor	mm/1000	62	66	70	ISO-534
Humedad	%	5.0	6.0	7.0	ISO-287
Alvura – Felt	ISO	95.9	98.0		ISO-2469
Opacidad	%	76.0	80.0		ISO-2471
Blancura (CIE)	D65 10°	158.0	161.0	164.0	ISO-11475
Coob 120s L1/L2	g/m ²		30	40	ISO-535

Recuerdos

JOSE ALEXANDRE PIOVAN
Process Production Assistant