
To : International Paper do Brasil Ltda.
Att :
Date : August 25th, 2020
Paper : **Chambril Digital 90.0**

		Minimum	Target	Maximum	
Grammage	g/m ²	86.4	90.0	93.6	ISO-536
Thickness	mm/1000	113	116	120	ISO-534
Moisture	%	4.1	4.5	4.9	ISO-287
Brightness – Felt	ISO	95.9	98.0		ISO-2469
Opacity	%	90.0	94.0		ISO-2471
Whiteness (CIE)	D65 10°	158.0	161.0	164.0	ISO-11475

Sincerely

JOSE ALEXANDRE PIOVAN
Process Production Assistant