

| STRUCTURE MEMBRANCE | | |
|--|--------------------------------------|---------------------------------|
| CHARACTERISTICS | DATA | TEST METHOD |
| Weight | 30oz/1050gsm | DIN EN ISO 2286-2 |
| Polyester Fabric | 1000x1000 denier 30X30 per inch | DIN EN ISO2060 DIN EN 1049-2 |
| Type of Coating | PVC | N/A |
| Tensile Strength | 4000N/5cm (L) | DIN EN ISO 1421 |
| | 3600N/5cm (W) | |
| Tear Strength | 550N (L) | DIN 53363 |
| | 500N (W) | |
| Adhesion Strength | 120N/5cm | DIN EN ISO 1421 |
| Low Temperature (available) | -22°F / -30°C | DIN EN 1876-1 |
| Fire Retardant (available) | Self-extinguishing, within 3 seconds | Internal Method |

| | |
|-------------------|--|
| ATTENTION: | The statements in this information sheet are based upon our knowledge and practical experience. The values are intended only as a source of information. A legally binding guarantee of specific properties is not to be inferred from our specifications. They are given without guarantee and do not constitute a warranty. The purchaser should independently determine, prior to use, the suitability of the material for his/her specific purpose. (Data represents averages and is not intended for use as a specification.) |
|-------------------|--|