

NO3310

One Way Vision

Description:

Film: 140micron; black & white PVC film
Adhesive: transparent adhesive
Liner: 160gsm white PEK paper with one side PE & Silicon coating
Width: 0.98/1.27/1.37/1.52m

Features:

1. One side visual, sun-shade and privacy protection; Hole size 1.60mm, perforation 40%;
2. Stable ink absorption and excellent dimensional stability.

Applications:

1. Applicable to glass surface, also applicable to transparent acrylic, PVC, PET transparent panels;
2. Suitable for various solvent ink and Eco-solvent ink.

Technical Data:

Testing condition: Indoor temperature $23\pm2^{\circ}\text{C}$; Relative humidity $50\pm5\%$; Use aluminum, glass, steel plate as the base material for testing.

Test Items	Units	Test method	Average value
Thickness PVC	Micron	GB/T6672-2001	140 ± 10
Weight-Liner	g/m^2	GB4669-1995	160 ± 10
Weight -finished product	g/m^2	GB4669-1995	290 ± 20
24h, 180°peel	N/25mm	FTM 1	≥ 4
Dimensional stability MD	mm	FTM 14	≤ 1.5
Dimensional stability CD	mm	FTM 14	≤ 1.0
Tensile strength MD	N/25 mm	GB/T1040.1-2006	≥ 25
Tensile strength CD	N/25 mm	GB/T1040.1-2006	≥ 20
Construction Temperature	$^{\circ}\text{C}$		20 ± 10
Applicable Temperature	$^{\circ}\text{C}$		$-20 \sim +70$

* All technical data is subject to change without prior notice.

Storage Condition:

All NAR products always need to be stored in the original packing and with the original protection materials, preferably stored hermetically, no more than 6 layers if stored horizontally. Do not expose in direct sunlight or heat sources. Shelf life will be one year with temperature of $25^{\circ}\text{C}\pm5^{\circ}\text{C}$ and relative humidity of $50\pm15\%$.

Production and Application Environment:

Production environment: temperature of $25\pm5^{\circ}\text{C}$, relative humidity of $50\pm10\%$, clean dust-free environment without suspended matter; Please move the materials to the printing environment 24 hours before printing. Test prior to use and remain enough edge margins when printing.
Application environment: temperature of $20\pm10^{\circ}\text{C}$, relative humidity of $50\pm10\%$; Pasting on flat, smooth and clean surface

without floating dust and shedding; It is necessary to take more than 2 hours for maintenance before laminating.

Warranty Condition :

1. One year shelf life: stored in suitable conditions, preferably use within 6 months;
2. One year prosecution period: from the product manufacture date, no-acceptance for overdue product.

Important Remarks:

1. The information mentioned in this product data sheet is based upon tests that were executed by NAR, and that we consider to be reliable. Environment humidity more than 70% in different district will decrease the printing result.

Product Application:

