

Technical Characteristics

TO

ATT. Controle de Qualidade

DATE : 21/05/2019

Alkaline Paper

		Minimum	Target	Maximum		
Blancura (CIE)	D65 10°	158,0	161,0	164,0	ISO-11475	N
Blancura (S/F)	ISO	96,0	98,0		ISO-2470	N
Cobb (60 Seg)	g/m ²		35,0	45,0	ISO-535	N
Espesor	mm	0,098	0,102	0,106	ISO-534	N
Gramage	g/m ²	76,8	80,0	83,2	ISO-536	N
Humedad	%	5,0	6,0	7,0	ISO-287	N
Opacidad	%	89,0	91,0		ISO-2471	N
Porosidad Gurley	s/100cc	7,0	12,0	18,0	TAPPI-460	N
Rugosidad F	mL/min		175,0	325,0	ISO-8791	N
Rugosidad T	mL/min		175,0	325,0	ISO-8791	N
Rugosidad (MP4) - F	ml/min	100,0	145,0	190,0	ISO-8791	N
Rugosidad (MP4) - T	ml/min	190,0	260,0	330,0	ISO-8791	N

Sincerely

JOAO CUSTODIO

Quality Control

PAPER - PAPEL CHAMBRIL 80.0

Shade

Conditioning of samples

Standard IPB
ISO 187/00
BIE080 - Rev. 3 - STD