

Technical Characteristics

TO

ATT. Controle de Qualidade

DATE : 21/05/2019

Alkaline Paper

		Minimum	Target	Maximum		
Brightness Felt(S/F)	ISO	96,0	98,0		ISO-2470	N
Cobb (60 sec)	g/m ²		35,0	45,0	ISO-535	N
Grammage	g/m ²	86,4	90,0	93,6	ISO-536	N
Moisture	%	5,0	6,0	7,0	ISO-287	N
Opacity	%	91,0	93,0		ISO-2471	N
Porosity Gurley	s/100cc	7,0	12,0	18,0	TAPPI-460	N
Roughness Bendtsen W	mL/min		175,0	325,0	ISO-8791	N
Roughness Bendtsen-F	mL/min		175,0	325,0	ISO-8791	N
Thickness	mm	0,110	0,114	0,118	ISO-534	N
Whiteness Felt	D65 10°	158,0	161,0	164,0	ISO-11475	N

Sincerely

JOAO CUSTODIO

Quality Control

PAPER - PAPEL CHAMBRIL 90.0

Shade

Conditioning of samples

Standard IPB
ISO 187/00
BIE090 - Rev. 4 - STD